



BUBBLE FREE GREY ADHESIVE CALENDERED VINYL

PRODUCT: SAV-180G

Description:

Soft Polymeric PVC film Color: White. Surface: Glossy.

Release paper:

Special Embossed PE coated silicone paper, 140g/sq.m 4oz/sq.yd

Adhesive:

Solvent polyacrylate, Removable, Grey Color.

MATERIAL DETAILS

PROPERTIES	TEST METHOD	METRIC	
Thickness (without protective paper and adhesive)	1	60 micron Polymeric PVC film/2.4mil	
Adhesive type	1	Solvent polyacrylate permanent Transparent	
Dimensional stability	FINAT TM14	Adhered to steel, No shrinkage in cross direction, in length 0.50mm max.	
Temperature resistance	1	Adhered to aluminum20°C to +65°C, no variation	
Seawater resistance	DIN 50021	Adhered to glass, after 48h/23°C no variation	
Adhesive power	FINAT TM1	After 24h, stainless steel 8-12N/25mm	
Tensile strength along acorss	ASTM D882-02;200MM/MIN	min.26MPa min.25MPa	
Elongation at break along across	ASTM D882-02;200MM/MIN	min 175% min 200%	
Shelf life	1	Up to 2 years	
Application temperature		Min.+10	
Service life by specialist application Under vertical outdoor exposure	1	Up to 3 years	
Available Size	1	42"/50"/54"/60" 50m	

INK PRINTABILITY

Solvent	Eco Solvent	UV	Latex
D			
Screen Printing	Dye Sublimation Transfer	Dye Sublimation Direct	Water based

NOTE: All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty

Soyang Technologies Co., Ltd (Soyang Headquarter)

West 19th FL, Yongtong Information plaza, No. 141 Huancheng Bei Road, Hangzhou City, Zhejiang PR., China.

www.soyang.net

P. 0086-571-28918690

F. 0086-571-28918695

Soyang Haining Factory

No.36 Jinniu Road, Jianshan District, Haining City, Zhejiang PR, China.

Soyang Hangzhou Factory

No,1199 Gongyuan Xi Rd, Fuyang, Hangzhou City, Zhejiang, PR, China

Soyang Europe Ltd

Calder House Metcalf Drive Altham Industrial estate Altham Lancashire BB5 5TU UK.

www.soyang.co.uk

P. 0044 (0) 161 765 3400 F. 0044 (0) 1282 772982