TECHNICAL DATA SHEET





GREY ADHESIVE CALENDERED VINYL

PRODUCT: SAV-140G

Description:

Soft Polymeric PVC film

Color: White.
Surface: Glossy.
Release paper:

PE coated silicone paper, 140g/sq.m 4oz/sq.yd

Adhesive:

Solvent polyacrylate, Removable, Grey Color.

MATERIAL DETAILS

MATERIAL DETAILS				
PROPERTIES	TEST METHOD	METRIC		
Thickness (without protective paper and adhesive)	1	100 micron Polymeric PVC film/4mil		
Adhesive type	1	Solvent polyacrylate permanent Transparent		
Dimensional stability	FINAT TM14	Adhered to steel, No shrinkage in cross direction, in length 0.50mm max.		
Temperature resistance	1	Adhered to aluminum20°C to +65°C, no variation		
Seawater resistance	DIN 50021	Adhered to glass, after 48h/23°C no variation		
Adhesive power	FINAT TM1	After 24h,stainless steel 8-12N/25mm		
Tensile strength along acorss	ASTM D882-02;200MM/MIN	min.26MPa min.25MPa		
Elongation at break along across	ASTM D882-02;200MM/MIN	min 175% min 200%		
Shelf life	1	Up to 2 years		
Application temperature		Min.+10		
Service life by specialist application Under vertical outdoor exposure	1	Up to 3 years		
Available Size	1	42"/50"/54"/60" 50m		

INK PRINTABILITY

Solvent	Eco Solvent	UV	Latex
0	0	0	0
Screen Printing	Dye Sublimation Transfer	Dye Sublimation Direc	t Water based

NOTE: All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty

Soyang Technologies Co., Ltd
(Sovang Headquarter)

West 19th FL, Yongtong Information plaza, No. 141 Huancheng Bei Road, Hangzhou City, Zhejiang PR., China.

www.soyang.net

P. 0086-571-28918690

F. 0086-571-28918695

Soyang Haining Factory

No.36 Jinniu Road, Jianshan District, Haining City, Zhejiang PR, China.

Soyang Hangzhou Factory

No,1199 Gongyuan Xi Rd, Fuyang, Hangzhou City, Zhejiang, PR, China

Soyang Europe Ltd

Calder House Metcalf Drive Altham Industrial estate Altham Lancashire BB5 5TU UK.

www.soyang.co.uk

P. 0044 (0) 161 765 3400

F. 0044 (0) 1282 772982