

Best-value Laminated Tent Fabric 15.8 oz/ 540gsm
PRODUCT: TFL1199B
FEATURES

- Good tensile and tear strength;
- Good ability on anti-UV, mouldproofing, antiabrasion and self-cleaning;
- Good stretch ability and softness;
- Good opacity.

APPLICATIONS

- Ideal for short-term mobile constructions.



SPECIFICATIONS		
Composition	1100Dtex *1100Dtex 3.5*3.5 /cm blockout	DIN 53830/DIN60001
	1000D *1000D 9*9/inch blockout	ASTM D 751
Weight	540 gsm +/- 20gsm	DIN53352
	15.8 oz	ASTM D 751
Lacquering	1/1 Acrylic (Upon request)	
Surface finish	Glossy	
Color	White	
Breaking Strength (Warp x Weft)	1579/1264N/5cm	DIN 53354
	358/287 lbs/2"	FS 5100
Tearing Strength (Warp x Weft)	357/306 N	DIN 53363
	81/69 lbs	FS 5100
Adhesion Strength	29.5N/5cm	DIN 53357
	6.7lbs/2"	FS 5970
Width	1000 ~ 3200mm	
	36" ~ 126"	
Fire Resistance	B1, B2, NFPA-701	
Temperature Resistance	- 30°C ~ 70°C	DIN 53372
	- 20°F ~ 158°F	FS 5874

NOTE: All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty

Soyang Technologies Co., Ltd
(Soyang Headquarters)

West 19th FL, Yongtong Information plaza, No. 141 Huancheng Bei Road, Hangzhou City, Zhejiang PR., China.

www.soyang.net

P. 0086-571-28918690

F. 0086-571-28918695

Soyang Haining Factory

No.36 Jinniu Road,Jianshan District,Haining City, Zhejiang PR,China.

Soyang Hangzhou Factory

No,1199 Gongyuan Xi Rd, Fuyang, Hangzhou City, Zhejiang, PR, China

Soyang Europe Ltd

Calder House Metcalf Drive
Altham Industrial estate
Altham Lancashire BB5 5TU UK

www.soyang.co.uk

P. 0044 (0) 161 765 3400

F. 0044 (0) 1282 772982