

Heat-Armor Tent Fabric

PRODUCT: TFK112323F

FEATURES

- High tensile and tear strength;
- Excellent ability on anti-UV, fire resistance, mould-proofing, anti-abrasion and self-cleaning;
- Good heat preservation performance.

APPLICATIONS

- Ideal for tents or fabric structures for heat preservation.



SPECIFICATIONS		
Composition	1100Dtex*1100Dtex 9*9/cm	DIN 53830/DIN60001
	1000D*1000D 23*23/inch	ASTM D 751
Weight	1300 gsm +/- 20 gsm	DIN53352
	38oz	ASTM D 751
Lacquering	1/0 Acrylin (upon request)	
Surface finish	Glossy	
Color	White or colors upon request	
Breaking Strength(Warp x Weft)	3500/3000 N/5cm	DIN 53354
	795/681 lbs/2"	FS 5100
Tearing Strength (Warp x Weft)	470/380 N/5cm	DIN 53363
	106/86 lbs/2"	FS 5100
Adhesion Strength	100 N/5cm	DIN 53357
	22.6 lbs/2"	FS 5970
Width	1000 ~ 3200 mm	
	36" ~ 126"	
Fire Resistance	B1, B2, NF-PA701	
Temperature Resistance	-30°C ~ 70°C	DIN 53372
	-20°F ~ 158°F	FS 5874

NOTE: All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty

Soyang Technologies Co., Ltd (Soyang Headquarters)

West 19th FL, Yongtong Information plaza, No. 141 Huancheng Bei Road, Hangzhou City, Zhejiang PR., China.

www.soyang.net

P. 0086-571-28918690

F. 0086-571-28918695

Soyang Haining Factory

No.36 Jinniu Road,Jianshan District,Haining City, Zhejiang PR,China.

Soyang Hangzhou Factory

No,1199 Gongyuan Xi Rd, Fuyang, Hangzhou City, Zhejiang, PR, China

Soyang Europe Ltd

Calder House Metcalf Drive
Altham Industrial estate
Altham Lancashire BB5 5TU UK

www.soyang.co.uk

P. 0044 (0) 161 765 3400

F. 0044 (0) 1282 772982