

OPP Back Standard One Way Vision 60/40

PRODUCT: SUNSHADE-SV64OPP
Description:

Perforated clear Monomeric PVC film, for use on even transparent substrates from glass, where two-way visual communication becomes possible. The ratio of the printable area of the total surface is about 60%.

Application:

For short and medium-term advertising graphics on shop windows, convenience store or other even surfaced transparent advertising media from glass.

Compatible inks:

Solvent, Eco-solvent, UV and Latex

MATERIAL DETAILS

PROPERTIES	TEST METHOD	RESULTS
Film thickness	ISO 4591:1992	160 micron clear PVC film
Adhesive type		Solvent polyacrylate, removable, transparent
Adhesive removability		Within 1 year residueless removable from most surface
Release paper		Perforated Liner+Transparent BOPP Liner
Diameter of hole	DIN 50021	1.5mm
Perforating ratio	FINAT TM1	40%
Dimensional stability	FINAT TM14	Adhered to glass, no shrinkage in cross direction, in length 0.3mm max
Temperature resistance		Adhered to glass, -20℃ to +65℃, no variation
Seawater resistance	DIN 50021	Adhered to glass, after 48h/23℃, no variation
Adhesive power	FINAT TM1	After 24h, stainless steel, 3-7N/25mm
Tensile strength along across	DIN EN ISO 527 DIN EN ISO 527	min. 5MPa min. 5MPa
Elongation at break along across	DIN EN ISO 527 DIN EN ISO 527	min 50% min 50%
Shelf life		1 year
Application temperature	Clean & dry surface	Min.+10℃
Service life by specialist application (Under vertical outdoor exposure)	Normal climate in China	Up to 2 years
Available width		1.06/1.27/1.37/1.52m
Regular length		50m

INK PRINTABILITY

Solvent	Eco Solvent	UV	Latex
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Screen Printing	Dye-sub Transfer	Dye-sub Direct	Water based

NOTE: All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty

Soyang Technologies Co., Ltd
(Soyang Headquarter)

West 19th FL, Yongtong Information plaza, No.
141 Huancheng Bei Road, Hangzhou City,
Zhejiang PR., China.

www.soyang.net

P. 0086-571-28918685

F. 0086-571-28918695

Soyang Technical Textile (zhejiang) Co.,Ltd

No.36 Jinniu Road,Jianshan District,Haining City, Zhejiang PR,China.

Hangzhou Soyang Flexible Material Co.,Ltd

No,1199 Gongyuan Xi Rd, Fuyang, Hangzhou City, Zhejiang, PR, China

Soyang Europe Ltd

Calder House Metcalf DriveAltham
Industrial estateAltham Lancashire BB5 5TU UK

www.soyang.co.uk

P. 0044 (0) 161 765 3400

F. 0044 (0) 1282 772982