



STANDARD ONE WAY VISION 1.0

PRODUCT: SUNSHADE-SV64 1.0

Features& Applications:

- 60/40 glossy white/black perforated PVC film, 1 mm holes
- Solvent polyacrylate transparent removable adhesive
- 185 gsm perforated paper + double sides PE coated paper
- Widely used as window graphics, building wraps, retail & commercial signage, POP displays,etc
- Compatible with Sol, Eco-sol, UV and Latex inks with high resolution printing & brillant image color

MATERIAL DETAILS

WATERIAL DETAILS			
PROPERTIES	TEST METHOD	METRIC	
Film thickness	ISO 4591:1992	180 micron white/black PVC film	
Adhesive type		Solvent polyacrylate transparent removable adhesive	
Removability		Within 1 year residueless removable from most surfaces	
Backing Paper		Perforated paper + Double Sides PE coated paper, 185 g/m²	
Dimensional stability	FINAT TM14	Adhered to glass, 0.2mm in cross direction, in length 1.0mm max.	
Temperature resistance		Adhered to glass, -20 $^{\circ}\!\mathrm{C}$ to +65 $^{\circ}\!\mathrm{C}$, no variation	
Diameter of hole		1.0mm	
Perforating Ratio		40%	
Seawater resistance	DIN 50021	Adhered to glass, after 48h/23 $^{\circ}{\mathbb{C}}$ no variation	
Adhesive power	FINAT TM 1, after 24h, stainless steel	3~7 N/25 mm	
Tensile strength along across	DIN EN ISO 527	min. 15 MPa min. 16 MPa	
Elongation at break along across	DIN EN ISO 527	min 120% min 140%	
Shelf life		1 year	
Application temperature		Min.+10℃	
Service life by specialist application Under vertical outdoor exposure (normal climate of China)		1 year	
Available Width		0.914/1.07/1.27/1.37/1.52m	
Regular Length		50m	

INK PRINTABILITY

Solvent	Eco Solvent	uv	Latex
Screen Printing	Dye-sub Transfer	Dye-sub Direct	Water based

NOTE: All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty

		1
Soyang Technologies Co., Ltd	Soyang Technical Textile (Zhejiang) Co., Ltd	Soyang Europe Ltd
(Soyang Headquarter)		
West 19th FL, Yongtong Information plaza, No.	No.36 Jinniu Road, Jianshan District, Haining City, Zhejiang PR, China.	Calder House Metcalf DriveAltham
141 Huancheng Bei Road, Hangzhou City,		Industrial estateAltham Lancashire BB5 5TU UK
Zhejiang PR., China.		
www.soyang.net	Hangzhou Soyang Flexible Material Co., Ltd	www.soyang.co.uk
www.soyang.nec	Transgariou boyang Frexible Material Co., Eta	www.soyang.co.ux
P. 0086-571-28918685		P. 0044 (0) 161 765 3400
F. 0086-571-28918695	No,1199 Gongyuan Xi Rd, Fuyang, Hangzhou City, Zhejiang, PR, China	F. 0044 (0) 1282 772982