

## Poly Deco

### ST-160T/ST-160D



Soyang's comprehensive range: PVC-Free. Supported by full industry chain. Compatible with various printing methods.

#### BRIEF DESCRIPTION

- 100% polyester warp-knitted fabric with natural cotton look
- Texturized hand feel, perfect as art deco & indoor deco (e.g. pillow cloth)

#### FEATURES



PVC-FREE



PHTHALATE FREE

#### INK PRINTABILITY



#### MATERIAL DETAILS

| PROPERTIES                     | TEST METHOD                              | METRIC                                   | IMPERIAL      |
|--------------------------------|--|--|---------------|
| Total Weight                   | DIN EN ISO 2286-2, ASTM D751             | 240 g/sq.m                               | 7.1 oz/sq.yd  |
| Base Fabric                    | DIN 60001, ASTM D7641                    | 100%polyester                            | 100%polyester |
| Weave Method                   | N/A                                      | Warp-knitted                             |               |
| Shrinkage                      | ISO 9866-2-1991                          | ≤2%                                      |               |
| Shielding Rate                 | ANSI PH2.19, ISO 5/2                     | 50%                                      |               |
| Flame Resistance               | DIN 4102-1-B1, NFPA 701 Test1, EN13501-1 | DIN 4102-1-B1, NFPA 701 Test1, EN13501-1 |               |
| Recommend Fixation Temperature | N/A                                      | 190°C, 30s                               |               |
| Width Available                | DIN EN ISO 3759, ASTM D751-2006          | Max 320cm                                | 126"          |
| Standard Length                | DIN EN ISO 3759, ASTM D751-2006          | 50m                                      | 55yds         |

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty.